



R.A.K. CERAMICS P.S.C.




TECHNICAL SPECIFICATION

MODEL	: 6GP SURFACE SERIES (R)
NOMINAL SIZE	: 60 X 60 CM (RECTIFIED)
THICKNESS	: 10.0 MM
TYPE OF PRODUCT	: GRES PORCELLANATO TILE
NATURE OF SURFACE	: GLAZED & RUSTIC
GROUP	: BIa
REF. STANDARD	: INTERNATIONAL STANDARD - ISO 13006:2012

TEST DESCRIPTION	STANDARD TEST METHOD	STANDARD REQUIREMENTS	R.A.K. CERAMICS SPECIFICATION
Surface Quality	BS EN ISO 10545 - 2	A minimum of 95% of the tiles are to be free from visible defects	Minimum of 95% of the tiles are free from visible defects
Length & Width	BS EN ISO 10545 - 2	± 0.6 %	± 0.15 %
Thickness	BS EN ISO 10545 - 2	± 5 %	± 5 %
Straightness of Sides	BS EN ISO 10545 - 2	± 0.5 %	± 0.2 %
Rectangularity	BS EN ISO 10545 - 2	± 0.6 %	± 0.2 %
Surface Flatness: Center Curvature	BS EN ISO 10545 - 2	± 0.5 %	± 0.25 %
Surface Flatness: Edge Curvature	BS EN ISO 10545 - 2	± 0.5 %	± 0.25 %
Surface Flatness: Warpage	BS EN ISO 10545 - 2	± 0.5 %	± 0.25 %
Water Absorption	BS EN ISO 10545 - 3	≤ 0.5 %	≤ 0.4 %
Breaking Strength	BS EN ISO 10545 - 4	≥ 1300 N	≥ 2000 N
Modulus of Rupture	BS EN ISO 10545 - 4	≥ 35 N/mm ²	≥ 40 N/mm ²
Coefficient of Linear Thermal Expansion	BS EN ISO 10545 - 8	Test method available	≤ 7 X 10 ⁻⁶ /°C
Resistance to Thermal Shock	BS EN ISO 10545 - 9	Test method available	No visible defect
Crazing Resistance	BS EN ISO 10545 - 11	Required	No crazing
Frost Resistance	BS EN ISO 10545 - 12	Required	No visible damage
Resistance to Household Chemicals & Swimming Pool Salts	BS EN ISO 10545 - 13	Minimum GB	Class GA No visible effect
Resistance to Low Concentrations Acids & Alkalis	BS EN ISO 10545 - 13	Manufacturer to state classification	Class GLA No visible effect
Resistance to Stains	BS EN ISO 10545 - 14	Minimum Class 3	Min. Class 4 Stains removed
Slip Resistance (Ramp Test)	DIN 51130 / DIN 51097	-	R11 / Class C

NOTE: This Technical Specification is applicable only to tiles in Choice "A".

Authorized:
For R.A.K. CERAMICS


RUEL PEREZ
General Manager
(QA/QC)

Date of Issue: 27/07/2014



PO. Box 4714, Ras Al Khaimah, United Arab Emirates

Tel : 00 - 971 - 7 - 2445046 Fax : 00 - 971 - 7 - 2445270 E-mail: rakceram@emirates.net.ae Http: //www.rakceram.com